



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B23K 35/40	A1	(11) International Publication Number: WO 00/38876 (43) International Publication Date: 6 July 2000 (06.07.00)
<p>(21) International Application Number: PCT/EP99/10248</p> <p>(22) International Filing Date: 21 December 1999 (21.12.99)</p> <p>(30) Priority Data: VE98A000048 23 December 1998 (23.12.98) IT</p> <p>(71) Applicant (for all designated States except US): TRAFILERIE DI CITTADELLA S.P.A. [IT/IT]; Via Mazzini, 57, I-35013 Cittadella (IT).</p> <p>(72) Inventor; and (75) Inventor/Applicant (for US only): ROCCO, Elio [IT/IT]; Via Mazzini, 57, I-35013 Cittadella (IT).</p> <p>(74) Agent: PIOVESANA, Paolo; Corso del Popolo, 70, I-30172 Venezia Mestre (IT).</p>		<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: METHOD FOR PRODUCING OPEN CORED WIRE FOR ELECTRIC ARC WELDING, AND PLANT FOR IMPLEMENTING THE METHOD</p> <div data-bbox="295 1171 1263 1318"> </div> <p>(57) Abstract</p> <p>A method for producing open cored wire for electric arc welding, in which a metal strip is subjected to a preliminary shaping stage to make it assume a concave profile suitable for filling with a welding powder mixture, said strip preliminary shaped in this manner then being filled with said powder mixture, and then subjected to a final shaping stage to join the longitudinal edges of said strip filled in this manner, to obtain an open cored wire which on termination of the process is fed to spooling and packaging, characterised by subjecting to said preliminary shaping stage a steel strip with a surface coating of a metal having a hardness less than and a coefficient of electrical conductivity greater than those of steel, then spooling and packaging the cored wire directly obtained from said final shaping stage.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

- 1 -

METHOD FOR PRODUCING OPEN CORED WIRE FOR ELECTRIC ARC WELDING, AND PLANT FOR IMPLEMENTING THE METHOD

This invention relates to a method for producing open cored wire for electric arc welding, and a plant for implementing the method.

5 Cored wire for electric arc welding is known. It is in the form either of open cored wire (non-welded) or closed cored wire (welded), depending on the method used for its production. Open cored wire is generally produced starting from steel strip which is firstly shaped to assume a U cross-section, then filled with a traditional powder mixture the purpose of which is to protect
10 the welding arc and to modify the quality of the steel forming the wire and of the materials to be welded. The strip shaped in this manner is then subjected to further shaping by which the two longitudinal edges of the strip are either brought into mutual contact or superimposed or clinched together, after which the cored wire obtained in this manner is rolled and drawn to attain its
15 required diameter.

Closed cored wire is also produced from steel strip, which is firstly shaped into a tube, is then welded along the contacting longitudinal edges, and is finally filled with the protective powder mixture.

Independently of whether the cored wire is open or closed, during its
20 shaping the steel strip is treated with liquid, powder or mixed lubricants, which facilitate the process. At the end of this process they have to be removed as they are detrimental to the welding, this removal being done by treatment in a bath in the case of closed wire, or by drying at high temperature (about 300°C) in the case of open wire, which cannot withstand immersion in the
25 bath.

- 2 -

After the outer surface of the cored wire has been perfectly cleaned, other lubricants not detrimental to welding can be applied to it to facilitate wire preservation and its sliding through the sheath of the welding machine.

Instead of applying these lubricants to the cored wire it can be
5 subjected to external copper, zinc or bronze plating to obtain the same advantage obtainable with the lubricants plus the advantage of better current passage given the high electrical conductivity of this coating material.

However this copper, bronze or other plating treatment represents a chemical or electrolytic treatment which in all cases is carried out after the
10 shaping process and after the removal of the lubricants required for this process, and can be effected only on closed cored wire in that it requires the wire to be immersed in a bath, which in the case of open wire would inevitably damage the powder.

An object of the invention is to produce open cored wire provided with
15 surface copper, bronze, zinc or other protective plating.

A further object is to produce open cored wire in a more rapid and economical form than otherwise achievable.

A further object is to provide open cored wire in which different extents of copper plating can be effected on its outer and inner surface.

20 These and further objects which will be apparent from the ensuing description are attained according to the invention by a method for producing open cored wire for electric arc welding as claimed in claim 1.

To implement the method, the invention proposes a plant as claimed in claim 7.

- 3 -

A preferred embodiment of the invention is described in detail hereinafter with reference to the accompanying drawing, which shows a schematic view of a plant according to the invention.

As can be seen from the drawing, the method of the invention is implemented within a line comprising a reel 2 on which a coil of steel strip 4 of characteristics corresponding to the cored wire to be produced is mounted, and a multi-station shaping line, with a first station 6 in which the strip is progressively shaped to assume a concave form suitable for receiving a traditional powder mixture in a filling station 8, and with a second station 10 in which the preshaped and filled strip 4 is transformed into a continuous tubular element, as the result of bringing the two longitudinal edges into mutual approach to an extent sufficient to retain the powder mixture.

In contrast to known production lines for open cored wire, in the line which implements the method of the invention there is provided upstream of the first shaping station 6 a copper plating station 12 for the steel strip 4, which consequently arrives at the entry to said first shaping station 6 provided on both surfaces with a copper coating.

This coating can be obtained chemically or electrolytically, by traditional methods.

Hence at the exit of the second shaping station 10 an open cored wire is obtained formed of copper plated steel strip enclosing in its interior the powder mixture, and ready to be wound into a spool.

The fact that the steel strip subjected to shaping has been previously copper plated has considerable advantages, and in particular:

- it enables open cored wire to be produced, this being a product easier to make than closed cored wire,

- 4 -

- it also uses the copper as lubricant during shaping and/or rolling, in place of traditional lubricants (stearates), hence eliminating substances which are a cause of impurities in the deposited material and can result in hot cracks in the weld seam,
 - 5 - it enables different extents of copper plating to be achieved on the two surfaces of the cored wire, so making it easier to control the copper quantity within the tolerances prescribed by international specifications for this type of wire,
 - it improves electrical contact during welding.
- 10 Instead of subjecting the steel strip to copper plating, it can be subjected to other coating treatment (for example bronze plating, zinc plating, etc.) with a different material having a hardness less than steel, to facilitate both the shaping of the steel strip and the sliding of the cored wire through the sheath of the welding machine, while at the same time having a better
- 15 coefficient of electrical conductivity than steel to improve electrical contact during welding.

 Again according to the invention, instead of starting with a steel strip to be subjected to protective metal coating prior to shaping, an already coated steel strip can be used as the raw material, obtained for example by rolling a

20 steel rod coated with the protective metal.

- 5 -


C L A I M S

1. A method for producing open cored wire for electric arc welding, in which a metal strip is subjected to a preliminary shaping stage to make it assume a concave profile suitable for filling with a welding powder mixture,
5 said strip preliminarily shaped in this manner then being filled with said powder mixture, and then subjected to a final shaping stage to join the longitudinal edges of said strip filled in this manner, to obtain an open cored wire which on termination of the process is fed to spooling and packaging, characterised by subjecting to said preliminary shaping stage a steel strip with
10 a surface coating of a metal having a hardness less than and a coefficient of electrical conductivity greater than those of steel, then spooling and packaging the cored wire directly obtained from said final shaping stage.
2. A method as claimed in claim 1, characterised by using a copper plated steel strip.
- 15 3. A method as claimed in claim 1, characterised by using a bronze plated steel strip.
4. A method as claimed in claim 1, characterised by using a zinc plated steel strip.
5. A method as claimed in claim 1, characterised by subjecting a steel
20 strip to chemical coating immediately before subjecting it to the preliminary shaping stage.
6. A method as claimed in claim 1, characterised by subjecting a steel strip to electrolytic coating immediately before subjecting it to the preliminary shaping stage.
- 25 7. A plant for implementing the method claimed in one or more of claims 1 to 6, comprising a steel strip unwinding station (2), a preliminary shaping

- 6 -

station (6) for giving the strip a concave profile suitable for filling with powder, a filling station (8) for said concave strip, and a final shaping station (10) for joining the longitudinal edges of said strip and for rolling it and drawing it to attain the predetermined diameter, characterised in that between the steel
5 strip unwinding station (2) and the preliminary shaping station (6) there is provided a station (12) for coating said strip with a layer of metal having a hardness less than and a coefficient of electrical conductivity greater than those of steel, immediately downstream of said final shaping station (10) there being provided a spooling station.

1/1



INTERNATIONAL SEARCH REPORT

Int. Patent Application No.
PCT/EP 99/10248

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B23K35/40

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 B23K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 002, no. 148 (C-030), 9 December 1978 (1978-12-09) & JP 53 112239 A (MATSUSHITA ELECTRIC IND CO LTD), 30 September 1978 (1978-09-30) abstract	1, 2, 5-7
X	PATENT ABSTRACTS OF JAPAN vol. 006, no. 126 (M-142), 10 July 1982 (1982-07-10) & JP 57 052595 A (NIPPON STEEL WELD PROD & ENG CO LTD), 29 March 1982 (1982-03-29) abstract	1, 2, 5-7
	--- -/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

19 May 2000

Date of mailing of the international search report

26/05/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Mollet, G

INTERNATIONAL SEARCH REPORT

Int. Patent Application No.
PCT/EP 99/10248

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 02, 29 February 1996 (1996-02-29) & JP 07 251289 A (KAWASAKI STEEL CORP), 3 October 1995 (1995-10-03) abstract -----	1,2,5-7
A	BE 777 588 A (SOUDURE AUTOGENE ELECT;ARCOS) 17 April 1972 (1972-04-17) claims 1,3,4 -----	1-4
A	US 4 203 188 A (BLANPAIN JACQUES ET AL) 20 May 1980 (1980-05-20) column 7, line 8 - line 12 -----	1-4

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 99/10248

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 53112239 A	30-09-1978	NONE	
JP 57052595 A	29-03-1982	NONE	
JP 07251289 A	03-10-1995	NONE	
BE 777588 A	17-04-1972	NONE	
US 4203188 A	20-05-1980	FR 2271898 A	19-12-1975
		AU 8032175 A	21-10-1976
		BE 827078 A	24-09-1975
		CH 591308 A	15-09-1977
		DE 2515342 A	04-12-1975
		ES 437873 A	16-01-1977
		GB 1485571 A	14-09-1977
		IT 1035793 B	20-10-1979
		JP 50160149 A	25-12-1975
		NL 7505156 A, B,	25-11-1975
		SE 423603 B	17-05-1982
		SE 7505806 A	24-11-1975
		SU 622390 A	30-08-1978
		US 4048705 A	20-09-1977
		US 4137446 A	30-01-1979
		ZA 7501905 A	25-02-1976